

# STEMELAN EPDMc A65

## Product data sheet

Revision date: 1.2.2017 - Version: 2.0



STEMPLAST HATZIAVGOSTIS  
ENGINEERING PLASTICS

Material:	ethylene propylene diene monomer (EPDM commercial)
ISO 1629:2013 Norm:	EPDM   ethylene propylene diene monomer
Product's shape:	semi-finished products

### Material characteristics

General purpose rubber, good elastic properties, good resistance to water, wider service temperature range (in comparison with SBR), moderate weather resistance, poor petroleum oil and solvent resistance.

### Application examples

General purpose applications, gaskets, O-rings.

### General properties

Density $\rho$	1.45 gr/cm <sup>3</sup>	DIN EN ISO 1183-1-A ASTM D792 sim.
Stress at 20% strain $\sigma$		ISO 37
Stress at 300% strain $\sigma$		DIN 53504-S2
Tensile strength $\sigma_T$	3.5 MPa	ASTM D412
Elongation at break $\epsilon_B$	250 %	
Tear strength (propagation resistance)		ISO 34-1B ASTM D624
Compression set (20 °C, 72 h) (70 °C, 24 h)	30 %	ISO 815-B DIN 53517 sim. ASTM D395 sim.
Hardness Shore scale A	65 $\pm$ 5	DIN EN ISO 7619-1 DIN 53505/ASTM D2240 sim.
Abrasion resistance		DIN EN ISO 4649-A DIN 53516/ASTM D5963 sim.
Volume resistivity $\rho$		IEC 60093 / VDE 0303-30
Surface resistivity $\sigma$		ASTM D257
Dielectric strength $E_d$		IEC 60243-1 / VDE 0303-21 DIN 53481 sim. / ASTM D149
Thermal conductivity $\lambda$		ISO 22007-2 / ISO 8302 sim. DIN 52612-2/ASTM C177 sim.
Service temperature long term	- 25 / 80 °C	

The indicated values result from numerous individual measurements for an approximation of the values and correspond to our today's knowledge. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallisation (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.